



*Porous Materials, Inc.*

20 Dutch Mill Road / Ithaca NY 14850 - 9785 / USA

February 14, 2014

Porous Materials, Incorporated has performed capillary flow porometry testing on Sample AllergyCare 100% Cotton for The Allergy Store. A bubble point pressure of 0.243 Psi with a pore diameter of 27.1879 microns was detected. The Mean Flow occurred at 1.437 Psi; this means that the average pore diameter is 4.5928 microns.

Testing completed by:

Evan W. Sorel

A handwritten signature in blue ink, appearing to read 'Evan W. Sorel', is written over a faint background image of a globe.

Lab Technician

*Not Just Products... Solutions*

**Tel:** 607-257-5544 / **Fax:** 607-257-5639 / **email:** [info@pmiapp.com](mailto:info@pmiapp.com) / **Toll Free:** 1-800-TALK-PMI (U.S. & Canada)

[www.pmiapp.com](http://www.pmiapp.com)